

NEUKADUR MultiCast 1

2-C PUR Fast Cast System

Very low viscosity, good impact strength

altropol

Main features

- very low-viscous
- easy to process
- low shrinkage
- good through-curing with a relatively long pot life

Applications

- production of negatives/positives
- universally for all kinds of moulds and patterns

Properties in the non-crosslinked state (approx. values)

		NEUKADUR MultiCast 1	NEUKADUR Hardener ISO 2	Unfilled mixture	Mixture filled with NEUKADUR filler B
Colour		beige	yellowish		
Mixing ratio	p.b.w.	100	100	-	350
Density (20 °C)	g/cm ³	0.95	1.10	1.05	1.6
Viscosity (20 °C)	mPa·s	35	75	55	2500

Properties of the mixture (approx. values)

		Unfilled mixture		Filled mixture
Pot life (RT, 100 g)	minutes	3.5		5.5
Demoulding time at 25°C	4 - 5 mm	minutes	75	45
	30 - 40 mm	minutes	-	30
Hardness	Shore D	DIN 53505	75	82
Colour			beige	beige

RT = room temperature

Mechanical values of the cured product (approx. values)

Tensile strength	MPa	DIN 53455	33	-
Tensile elongation	%	DIN 53455	6	-
Flexural strength	MPa	DIN 53452	33	35
Bending elongation	%	DIN 53452	-	3
Modulus in flexure	MPa	DIN 53457	650	2650
Impact strength	kJ/m ²	EN ISO 179	14	5
Compressive strength	MPa	DIN 53454	-	80
Linear dimensional change	%	500 x 50 x 25mm	-	0.15

How to process the material

Before using NEUKADUR MultiCast 1, mix the same thoroughly until it has got a homogeneous appearance.

Mix both components thoroughly with each other at room temperature (>18°C) according to the indicated mixing ratio. Before casting make sure that parts and moulds are free from humidity and non-evaporated release agent.

For layers with a thickness of >5 mm, we recommend the use of fillers, e. g. NEUKADUR filler B.

We also recommend sharing out the quantity of filler between both components.

For release agents, please visit our homepage under <http://www.altropol.de/en/produkte/weitere-produkte/trennmittel/>

NEUKADUR MultiCast 1

2-C PUR Fast Cast System
Very low viscosity, good impact strength

altropol

Form of delivery

NEUKADUR MultiCast 1	1 kg	5 kg	10 kg	30 kg	200 kg
NEUKADUR Hardener ISO 2	1 kg	5 kg	10 kg	30 kg	200 kg
NEUKADUR filler B	5 kg	10 kg	25 kg		

Storage

We recommend keeping the material in tightly closed original receptacles at temperatures of 20 - 25 °C. When duly stored, the material can be used within the shelf life indicated on the labels (the first 2 digits of the batch number indicate the week, the 3rd digit indicates the year).

Measure of precaution

With the aid of the current safety data sheets, which contain physical, ecological, toxicological and other data relating to safety, the user can inform himself on the safe handling and storage of the products.

Our technical service - in words, in writing or by trials - is given according to the current state of our knowledge. It does however not relieve the customer/user from the duty to check by himself if the products supplied by us are suitable for the intended processes and purposes. Application, use and processing of the products take place beyond our control possibilities and lie therefore exclusively in the area of responsibility of the processor. Any existing property rights of third parties are to be considered. We guarantee the perfect quality of our products in accordance with our general terms and conditions of business. When handling our products you have to observe the legal rules and the rules for the industrial hygiene. As for the rest, we refer to the corresponding safety data sheets.

• 2017-12-05.3 / 12 / LW-W •

• www.altropol.de •

• Altropol Kunststoff GmbH • Rudolf-Diesel-Straße 9 - 13 • D-23617 Stockelsdorf • Tel. +49 451-499 60-0 •
• Fax. +49 451-499 60-20 • E - Mail: info@altropol.de •